


ProCon-F-E Virgin Polypropylene, Fibrillated Fiber Tape



COST EFFECTIVE FIBER REINFORCEMENT

ProCon-F-E, a cost-effective fiber, provides plastic shrinkage and settlement crack control, increased impact resistance and increased residual strength

ProCon-F-E Physical Properties

Filament Diameter	0.03" (0.76 mm)
Fiber Length	0.75" (19mm) or 1.5" (38mm)
Specific Gravity	0.91
Tensile Strength	44 ksi (300 MPa)
Flexural Strength	700 ksi (4.9 GPa)
Melting Point	v320° F (160° C)
Color	White
Water Absorption	Nil
Alkali Resistance	Excellent
Concrete Surface	Commercial
Corrosion Resistance	High

Description

ProCon-F-E fibrillated tape fiber products are designed to distribute quickly through the concrete matrix. Our fibrillated tape product is designed to optimize the mechanical bond between the mortar and the fiber. ProCon-F-E is used in concrete products for the purpose of controlling plastic shrinkage and thermal cracking.

ProCon-F-E meets the requirements of ASTM C-1116, Section 4.1.3 and AC-32 at 1.5 lb (0.68 kg) per CY.

Applications

ProCon-F-E utilizes the mixing activity to disperse the fibers into the mix. ProCon-F-E provides a multi-dimensional fiber network and does not affect curing process chemically.

ProCon-F-E can be used in all types of concrete. Fibrillated tape synthetic fibers help the concrete and can be used to replace light gauge WWF, depending on the application

800-456-9266

www.nycon.com

sales@nycon.com

ProCon-F-E

Virgin Polypropylene, Fibrillated Fiber Tape



Advantages/Benefits	<ul style="list-style-type: none">• Mechanical bond with the concrete• Reduces the formation of plastic shrinkage cracking in concrete.• Provides multi-dimensional reinforcement.• Improves impact, shatter and abrasion resistance of concrete.• Enhances durability and toughness of concrete.
Mixing	ProCon-F-E can be added directly to the mixing system after the batching of the ingredients and mixed at high speed for a minimum of three minutes. The addition of ProCon-F-E at the normal recommended dosage rate of 1.5 lb/cy does not require any mix design or application changes. A water reducer or super-plasticizer is recommended in concrete products where improved workability and finishability are desired.
Tooling & Finishing	Fiber reinforced concrete can be finished by most finishing techniques. ProCon-F-E mixes can be pumped and placed using conventional equipment. Hand screeds can be used, but vibratory and laser screeds are recommended to provide added compaction and bury surface fibers.
Packaging	(30) 1 lb (0.45 kg) bags per box, 600 lbs per pallet (20) 1.5 lb (0.68 kg) bags per box, 600 lbs per pallet ProCon-F-E Fibers are packaged in pre-measured 1 lb or 1.5 lb degradable "toss-in" paper beater bags or water soluble bags.
Storage and Shelf Life	ProCon-F-E should be stored in dry warehouse. Protect product from the rain.

KEEP CONTAINER TIGHTLY CLOSED - KEEP OUT OF REACH OF CHILDREN - NOT FOR INTERNAL CONSUMPTION - FOR INDUSTRIAL USE ONLY

All information provided by Nycon Corporation concerning Nycon products, including but not limited to, any recommendations and advice relating to the application and use of Nycon products, is given in good faith based on Nycon's current experience and knowledge of its products when properly stored, handled and applied under normal conditions in accordance with Nycon's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual site conditions and other factors outside of Nycon's control are such that Nycon assumes no liability for the provision of such information, advice, recommendations or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations or instructions related to its products. The user of the Nycon product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s).

Nycon reserves the right to change the properties of its products without notice. All sales of Nycon product(s) are subject to its current terms and conditions of sale which are available at www.nycon.com or by calling 800-456-9266.

Prior to each use of any Nycon product, the user must always read and follow the warnings and instructions on the product's most current Technical Data Sheet, product label and Material Safety Data Sheet which are available. Nothing contained in any Nycon materials relieves the user of the obligation to read and follow the warnings and instruction for each Nycon product as set forth in the current Product Data Sheet, product label and Material Safety Data Sheet prior to product use.

Nycon warrants this product for one year from date of shipment to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. Nycon SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. Nycon SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

800-456-9266

www.nycon.com

sales@nycon.com